

**AMENDMENTS TO THE CLAIMS:**

Claims 1 - 123 (Canceled)

124. (Currently amended) A medical prosthesis for use within a body, said prosthesis being formed of radiation treated ultra high molecular weight polyethylene having cross-links and multiple melting peaks, wherein the multiple melting peaks are a result of irradiation-generated heat, thereby reducing crystallinity of the ultra high molecular weight polyethylene, **and wherein the polyethylene has a tensile elastic modulus of less than about 1 GPa.**
125. (Previously presented) The medical prosthesis of claim 124, wherein said ultra high molecular weight polyethylene has three melting peaks.
126. (Previously presented) The medical prosthesis of claim 124, wherein said ultra high molecular weight polyethylene has two melting peaks.
127. (Previously presented) The medical prosthesis of claim 124, wherein said ultra high molecular weight polyethylene has been subjected to heating by irradiation.
128. (Previously presented) The medical prosthesis of claim 124, wherein said polymeric structure has extensive crosslinking so that a substantial portion of said polymeric structure does not dissolve in xylene at 130°C or DECALIN at 150°C over a period of 24 hours.
129. (Previously presented) The medical prosthesis of claim 124, wherein said ultra high molecular weight polyethylene has an initial average molecular weight of greater than about 1 million.

130. (Previously presented) The medical prosthesis of claim 124, wherein said prosthesis is constructed and arranged for replacement of a joint selected from the group consisting of a hip joint, a knee joint, an elbow joint, a shoulder joint, an ankle joint and a finger joint.
131. (Previously presented) The medical prosthesis of claim 124, wherein said ultra high molecular weight polyethylene has a polymeric structure with less than about 50% crystallinity and less than about 940 MPa tensile elastic modulus, so as to reduce production of fine particles from said prosthesis during wear of said prosthesis.
132. (Currently amended) Radiation treated ultra high molecular weight polyethylene having multiple melting peaks and cross-links, wherein the multiple melting peaks are a result of irradiation-generated heat, thereby reducing crystallinity of the ultra high molecular weight polyethylene, **and wherein the polyethylene has a tensile elastic modulus of less than about 1 GPa.**
133. (Previously presented) The ultra high molecular weight polyethylene of claim 132, wherein said ultra high molecular weight polyethylene has three melting peaks.
134. (Previously presented) The ultra high molecular weight polyethylene of claim 132, wherein said ultra high molecular weight polyethylene has two melting peaks:
135. (Previously presented) The ultra high molecular weight polyethylene of claim 132, wherein said ultra high molecular weight polyethylene has been subjected to heating by irradiation.
136. (Previously presented) The ultra high molecular weight polyethylene of claim 132, wherein said ultra high molecular weight polyethylene has a unique

polymeric structure characterized by less than about 50% crystallinity and less than about 940 MPa tensile elastic modulus.

137. (Withdrawn) A method for making a cross-linked ultra high molecular weight polyethylene having multiple melting peaks, comprising the steps of: heating ultra high molecular weight polyethylene having polymeric chains to a temperature below the melting point of the polyethylene; irradiating said ultra high molecular weight polyethylene so as to cross-link said polymeric chains; and cooling said irradiated ultra high molecular weight polyethylene.
138. (Withdrawn) The method of claim 137, wherein said ultra high molecular weight polyethylene in said providing step is heated to a temperature above room temperature but below the melting temperature of said ultra high molecular weight polyethylene.
139. (Withdrawn) A method for making a cross-linked ultra high molecular weight polyethylene, comprising the steps of:  
heating ultra high molecular weight polyethylene having polymeric chains to a temperature below the melting point of the polyethylene; irradiating said ultra high molecular weight polyethylene so as to (1) cross-link said polymeric chains and (2) to generate sufficient heat to at least partially melt the ultra high molecular weight polyethylene; and cooling said irradiated ultra high molecular weight polyethylene.
140. (Withdrawn) A method for making cross-linked ultra high molecular weight polyethylene, comprising the steps of: heating ultra high molecular weight polyethylene to a temperature of no more than about 90°C; irradiating said ultra high molecular weight polyethylene to cross-link the ultra high molecular weight polyethylene and to generate sufficient heat to at least partially melt the ultra high molecular weight polyethylene; and cooling said irradiated ultra high molecular weight polyethylene.

141. (Withdrawn) A method for making cross-linked ultra high molecular weight polyethylene, comprising the steps of: heating ultra high molecular weight polyethylene at a temperature ranging from about 90°C to below the melting point; irradiating said ultra high molecular weight polyethylene to cross-link the ultra high molecular weight polyethylene and to generate sufficient heat to at least partially melt the ultra high molecular weight polyethylene; and cooling said irradiated and heated ultra high molecular weight polyethylene.
142. (Withdrawn) A method for making a cross-linked ultra high molecular weight polyethylene having substantially no detectable free radicals, comprising the steps of: heating ultra high molecular weight polyethylene having polymeric chains to a temperature below the melting point of the polyethylene; irradiating said ultra high molecular weight polyethylene with more than 5 Mrads of radiation so as to cross-link said polymeric chains, wherein the radiation heats the ultra high molecular weight polyethylene; and cooling said heated ultra high molecular weight polyethylene.
143. (Withdrawn) The method of claim 142, wherein the final temperature of said ultra high molecular weight polyethylene after said irradiation step is above the melting temperature of said ultra high molecular weight polyethylene.
144. (Withdrawn) A method of making a medical prosthesis from radiation treated ultra high molecular weight polyethylene having multiple melting peaks, said prosthesis resulting in the reduced production of particles from said prosthesis during wear of said prosthesis, comprising the steps of: providing radiation treated ultra high molecular weight polyethylene having multiple melting peaks; and forming a medical prosthesis from said ultra high molecular weight polyethylene so as to reduce production of particles from said prosthesis during wear of said prosthesis, said ultra high molecular weight polyethylene forming a load bearing surface of said prosthesis.
145. (Withdrawn) A method of making a medical prosthesis from radiation treated

ultra high molecular weight, said prosthesis resulting in the reduced production of particles from said prosthesis during wear of said prosthesis, comprising the steps of:

providing ultra high molecular weight polyethylene that has been irradiated above room temperature at a dose rate of at least 2 Mrads/hour; and forming a medical prosthesis from said ultra high molecular weight polyethylene so as to reduce production of particles from said prosthesis during wear of said prosthesis, said ultra high molecular weight polyethylene forming a load bearing surface of said prosthesis.

146. (Withdrawn) A method of making a medical prosthesis from radiation treated ultra high molecular weight, said prosthesis resulting in the reduced production of particles from said prosthesis during wear of said prosthesis, comprising the steps of:

providing ultra high molecular weight polyethylene that has been irradiated above room temperature at a dose rate of at least 4 Mrads/hour; and forming a medical prosthesis from said ultra high molecular weight polyethylene so as to reduce production of particles from said prosthesis during wear of said prosthesis, said ultra high molecular weight polyethylene forming a load bearing surface of said prosthesis.

147. (Withdrawn) A method for making a cross-linked polyethylene, comprising the steps of: heating polyethylene at a temperature that is below its melting point; irradiating the polyethylene so as to (1) cross-link polymeric chains in the polyethylene and (2) to generate sufficient heat to at least partially melt the polyethylene; and cooling the irradiated polyethylene.

148. (Withdrawn) The method according to claim 147, wherein the irradiation melts the polyethylene.

149. (Withdrawn) The method according to claim 147, wherein the partially melted polyethylene is further heated by an additional heating source.